

ICF-16SB-TX

MERV 16, 100% Spunbond polyester with laminated ePTFE membrane.



ICF-16SB-TX

is a high strength, 100% synthetic spunbonded media with a laminated ePTFE membrane. Provides high filtration efficiency with excellent durability and moisture resistance.

Specifications	
Basis Weight (gram/ounces)	260 g/m ² 8oz.
Air Permeability	3-6 cfm/ft ² @ 0.5 wc
Mullen Burst Dry	250 psi
Mullen Burst Wet	250 psi

Test Results	
Airflow Rate (CFM)	500
Initial Resistance (in WG)	1.25
E1 (%) Initial Efficiency 0.30 -1.0 um	99.987
E2 (%) Initial Efficiency 1.0 -3.0 um	100
E3 (%) Initial Efficiency 3.0 10.0 um	100
MERV Rating	16

Applications
Powder Coating
Pharmaceutical
Pneumatic Conveying
Food Processes
Paint Pigment